

Chapitre 7 - Configurer la transparence Aero Glass

Documentation de Chapitre 7 - Configurer la transparence Aero Glass.

- [Écrire les réglages](#)
- [Recharger les effets](#)
- [Vérifier](#)
- [Valeurs recommandées](#)

Écrire les réglages

Écrire les réglages

```
kwriteconfig6 --file kwinrc \  
  --group Plugins \  
  --key aeroglassblurEnabled true
```

```
kwriteconfig6 --file kwinrc \  
  --group Plugins \  
  --key blurEnabled false
```

```
kwriteconfig6 --file kwinrc \  
  --group Plugins \  
  --key contrastEnabled false
```

```
kwriteconfig6 --file kwinrc \  
  --group Effect-aeroglassblur \  
  --key EnableTransparency true
```

```
kwriteconfig6 --file kwinrc \  
  --group Effect-aeroglassblur \  
  --key BasicColorization false
```

```
kwriteconfig6 --file kwinrc \  
  --group Effect-aeroglassblur \  
  --key MaximizeColorization false
```

```
kwriteconfig6 --file kwinrc \  
  --group Effect-aeroglassblur \  
  --key BlurStrength 3
```

```
kwriteconfig6 --file kwinrc \  
  --group Effect-aeroglassblur \  
  --key AeroIntensity 50
```

```
kwriteconfig6 --file kwinrc \  
  --group Effect-aeroglassblur \  
  --key ReflectionIntensity 75
```

Recharger les effets

Recharger les effets

```
qdbus6 org.kde.KWin /Effects unloadEffect blur  
qdbus6 org.kde.KWin /Effects unloadEffect contrast  
qdbus6 org.kde.KWin /KWin reconfigure  
qdbus6 org.kde.KWin /Effects loadEffect aeroglassblur
```

Vérifier

Vérifier

```
qdbus6 org.kde.KWin /Effects isEffectLoaded aeroglassblur
```

Résultat attendu :

```
true
```

Lister les effets Aero détectés :

```
qdbus6 org.kde.KWin /Effects listOfEffects | grep -i aero
```

Valeurs recommandées

Valeurs recommandées

Paramètre	Valeur	Fonction
BlurStrength	3	Intensité du flou
AeroIntensity	50	Intensité de la couleur
ReflectionIntensity	75	Intensité du reflet
EnableTransparency	true	Active la transparence
BasicColorization	false	Conserve l'Aero complet
MaximizeColorization	false	Évite l'opacité en maximisé